

287 GPS™ General-Purpose Solid Wire Solder

- Very high purity
- Low working temperature
- High strength



SPECIFICATIONS

Joint strength..... up to 7,000 psi/48 MPa
Working temperature..... 414°F/212°C

PROCEDURES

Follow standard soldering techniques. Any heat source can be used. Clean the base metal as thoroughly as possible; heavy dirt should be removed. Pre-flux the solder area. Heat the base metal directly. Touch solder to the base metal to start flow. Remove flux residue.

APPLICATIONS

- Potting cable ends
- Sewer pipe
- Tinning
- Radiator repair

Code #	Description	Package
287-4-0000	1/8"	1 lb spool
381-0-0000	Scavenger™ Flux	1 pt
383-0-0000	#383 Acid Paste Flux	1.7 oz



Available in select sizes only

Note: Not for use on electrical or electronic applications. Not for use on potable water.